

BOLD - REKLAMA,POLIGRAFIA
44-100 Gliwice
Sowińskiego 11
Poland

Measurement of photoluminescence according to DIN 67510-1:2009

(2 appendices)

Identification

Object	One photoluminescent exit sign with “LunaCLASSIC” layer, size 200 × 380 mm. See pictures in appendix 1.
Object state	Upon arrival the object had no visual damages.
Location	Borås, Sweden
Measurement date	May 29–31, 2018

Measurement methods and procedures

The measurements follows RISE method 2515 in applicable parts. The sample was exposed during a time of 5 minutes at 1000 lux from an unfiltered 150 W xenon lamp. The illuminance at the measuring plane was measured with a luxmeter, Hagner, Model S4. After 5 minutes the xenon lamp was turned off and a luminance meter, Photo Research Model 1980A, connected to a computer, was recording the luminance every minute for 10 hours. A measuring spot of about \varnothing 40 mm was used. The sample was kept under dark conditions for at least 48 h prior to excitation.

The colour during excitation and attenuation was measured with a spectrometer, Spectrascan PR-735. The excitation was done with the above light source at 1000 lux for 5 minutes and the attenuation colour measurement started about 15 seconds after the lamp was switched off.

In accordance with section 4.5 in DIN 67510-1, a logarithmic parabolic extrapolation of the results was made in order to determine the time when the luminance is $0,3 \text{ mcd/m}^2$, the decay time.

Measurement conditions

Room temperature	$(23 \pm 1) \text{ }^\circ\text{C}$
Relative humidity	$(45 \pm 5) \%$
Illumination	1000 lx perpendicular to the sample, Xenon lamp

Results

The results only refer to the object specified in this document.

RISE Research Institutes of Sweden AB

Postal address	Office location	Phone / Fax / E-mail
Box 857 SE-501 15 BORÅS Sweden	Brinellgatan 4 SE-504 62 BORÅS	+46 10 516 50 00 +46 33 13 55 02 info@ri.se

This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

Table 1: Compilation of the results for luminance and calculated decay time.

Sample ID	Luminance (mcd/m ²)					Decay time (min)
	2 min	10 min	30 min	60 min	120 min	
LunaCLASSIC	1180	240	72,0	32,3	13,9	2370

Table 2: CIE 1931 chromaticity coordinates for 2° standard observer.

Sample ID	During excitation		During attenuation	
	x	y	x	y
LunaCLASSIC	0,342	0,372	0,277	0,564

Measuring uncertainty

The measuring uncertainty is $\pm 5\%$ of the measured luminance values, but not less than $\pm 0,05$ mcd/m². The uncertainty of the given values for x and y is $\pm 0,005$.

The reported expanded uncertainty of measurement is stated as the standard uncertainty of measurement multiplied by the coverage factor $k = 2$, which for a normal distribution corresponds to a coverage probability of approximately 95%. The standard uncertainty has been determined in accordance with EA Publication EA-4/02.

Equipment

Xenon-lamp 150 W, SP inv.no. 502959
 Luminance meter Pritchard PR 1980, SP inv.no. 500721
 Luxmeter Hagner S4, SP inv.no. 901737
 Spectrometer Spectrascan PR-735, SP inv.no. 901491

RISE Research Institutes of Sweden AB Measurement Science and Technology - Time and Optics

Performed by

Examined by

Maria Nilsson Tengelin

Stefan Källberg

Appendices


Pictures of the test object
 Measured luminance, table and diagram

Appendix 1

Pictures of the test object

Exit sign LunaCLASSIC



 = Measuring position

Exit sign – printed text, bottom left corner



Exit sign – printed text, bottom right corner



Appendix 2

Measured luminance, table and diagram

Table 1. Luminance during attenuation (after 5 min exposure at 1000 lux).

Time (min)	Luminance (mcd/m ²)	Time (min)	Luminance (mcd/m ²)
5	490	65	29,3
10	240	70	26,8
15	155	75	24,8
20	113	80	22,9
25	88,3	85	21,3
30	72,0	90	19,9
35	60,2	95	18,6
40	51,7	100	17,4
45	45,2	105	16,4
50	40,1	110	15,5
55	35,7	115	14,7
60	32,3	120	13,9

Diagram 1. Luminance during attenuation (after 5 min exposure at 1000 lux).

